

Semmelmann, Theresa et al.

Working Paper

How to avoid fracture of the locking screw in modular revision arthroplasty of the hip using the MRP Titan Revision System

Weidener Diskussionspapiere, No. 77

Provided in Cooperation with:

University of Applied Sciences Amberg-Weiden (OTH)

Suggested Citation: Semmelmann, Theresa et al. (2020) : How to avoid fracture of the locking screw in modular revision arthroplasty of the hip using the MRP Titan Revision System, Weidener Diskussionspapiere, No. 77, ISBN 978-3-937804-79-8, Ostbayerische Technische Hochschule Amberg-Weiden (OTH), Weiden i.d.OPf.

This Version is available at:

<https://hdl.handle.net/10419/228719>

Standard-Nutzungsbedingungen:

Die Dokumente auf EconStor dürfen zu eigenen wissenschaftlichen Zwecken und zum Privatgebrauch gespeichert und kopiert werden.

Sie dürfen die Dokumente nicht für öffentliche oder kommerzielle Zwecke vervielfältigen, öffentlich ausstellen, öffentlich zugänglich machen, vertreiben oder anderweitig nutzen.

Sofern die Verfasser die Dokumente unter Open-Content-Lizenzen (insbesondere CC-Lizenzen) zur Verfügung gestellt haben sollten, gelten abweichend von diesen Nutzungsbedingungen die in der dort genannten Lizenz gewährten Nutzungsrechte.

Terms of use:

Documents in EconStor may be saved and copied for your personal and scholarly purposes.

You are not to copy documents for public or commercial purposes, to exhibit the documents publicly, to make them publicly available on the internet, or to distribute or otherwise use the documents in public.

If the documents have been made available under an Open Content Licence (especially Creative Commons Licences), you may exercise further usage rights as specified in the indicated licence.

Die Hochschule im Dialog:

How to avoid fracture of the locking screw in modular revision arthroplasty of the hip using the MRP Titan Revision System

Theresa Semmelmann
Alexander Schuh
Horst Rottmann
Reinhard Schröder
Christopher Fleischmann
Stefan Sesselmann

How to avoid fracture of the locking screw in modular revision arthroplasty of the hip using the MRP Titan Revision System

Theresa Semmelmann (1)

Alexander Schuh (2)

Horst Rottmann (3, 4)

Reinhard Schröder (5)

Christopher Fleischmann (1)

Stefan Sesselmann (1)

(1) Institute for Medical Technology, Ostbayerische Technische Hochschule (OTH) Amberg-Weiden, Hetzenrichter Weg 15, 92637, Weiden, Germany

Communicating author: s.sesselmann@oth-aw.de, Phone: +49 (961) 382-1624

(2) Musculoskeletal Center Neumarkt, Neumarkt Hospital, Nürnberger Str. 12, 92318 Neumarkt, Germany

(3) Faculty of business administration, Ostbayerische Technische Hochschule (OTH) Amberg-Weiden, Hetzenrichter Weg 15, 92637, Weiden, Germany

(4) ifo Institute – Leibniz Institute for Economic Research at the University of Munich

(5) Peter Brehm GmbH, Am Mühlberg 30, 91085 Weisendorf, Germany

Keywords: MRP Titan, Fracture, Hip, Modular Stem, Locking Screw

Abstract

The use of modular femoral stems in primary and revision arthroplasty of the hip has become popular within the last decade. On the other hand modularity creates new potential problems like fretting, crevice and galvanic corrosion, component loosening, dissociation and fracture of modular prostheses. Recently a problem of fracture of a locking screw in revision arthroplasty of the hip using the MRP Titan Stem (Peter Brehm GmbH, Weisendorf, Germany) appeared. The aim of this study is to evaluate the meaning of surface contamination in respect to fracture mechanism. To avoid fracture of the screw M6 of the MRP Titan System we recommend cleaning the inner thread of the morse taper junction with saline solution before junction is fixed with the screw and the torque wrench.

1. Introduction

The use of modular femoral stems in primary and revision arthroplasty of the hip has become popular within the last decade because of the advantage of more flexibility and optimization of femoral anteversion, limb length, and femoral component offset. In several studies good mid- to long- term results have been published for the MRP Titan Revision Stem in revision arthroplasty of the hip [1, 2, 3, 4, 29]. Modularity also provides intraoperative flexibility when partial hip implant revision is required. On the other hand modularity creates new potential problems and complications which should be taken into account. Micromovement, component loosening, fretting, crevice and galvanic corrosion, fracture and dissociation of modular prostheses in primary and revision hip arthroplasty have been published [5-17].

Recently a recurrent fracture of the cone of the morse taper junction of the MRP Stem in an Obese Patient has been published [15]. In this case intraoperatively a fractured locking screw could be found.

Grupp et al. [16] postulated surface contamination as a risk factor for modular titanium alloy neck adapter failures in hip replacement.

The aim of this study was to evaluate the meaning of surface contamination in respect to fracture of the locking screw of the MRP Titan Revision System (Peter Brehm GmbH, Weisendorf, Germany).

2. Material and Methods

The modular MRP Titan Revision System based on modular taper connections designed for cementless implantation with initial distal diaphyseal fixation. The implant components are made of a titanium alloy (Ti6Al4V) with a rough corundum-blasted surface with a roughness of 40-60 μm to facilitate osseous integration. The modular design essentially consists of three components:

- The distally tapered femoral stem with longitudinal parabolic ribs for fixation with rotational stability. The stem is available as a straight-stem model in 140 mm and 200 mm length, and curved-stem version to fit the physiologic anterior bow of the femur in 200 mm length. 260 mm and 320 mm curved stems with two distal transverse drill holes are also available, providing the possibility to use distal locking bolts for additional stability. Diameters are available in 1 mm increments between 13 and 22 mm.
- Three different neck models (length 50, 60, and 70 mm) with a standard taper (Euro taper 12/14). The neck components are available with different neck-stem angles of 130° (37 mm

offset) and 123° (47 mm offset).

– An optional extension sleeve, adding 30 mm to the neck length. The continuously adjustable taper connections are locked intraoperatively with a titanium-nitride coated locking screw using an implant-specific torque wrench 25 Nm.



Fig. 1: The MRP-TITAN System with the lockingscrew (gold)

The locking screw M6 (Fig. 2) is made from Ti6Al4V alloy according to ASTM and DIN ISO [18-21]. The screw is 25 mm long, whereas the screw shaft measures 17 mm, thread length is 12 mm with 12 threads. The screw is titanium-nitride coated to reduce sliding friction [22]. During the fixation process titanium-nitride coating shows smooth abrasion.




Fig. 2: Sectional view through the test specimen,

To evaluate the influence of contamination the inner tread of the morse taper junction in respect to fracture of the titanium nitrid coated locking screw M6 of the MRP Titan system was in vitro tested.

A MRP-stem model with the male component of the morse taper junction was fixed in a jaw

vice. The model stems and necks were assembled and fixed with the elocking screw using the original implant devices. In sum 134 screws, model stems and model necks were tested.

To investigate the influence of NaCl solution on fixing the locking screw a preliminary study was conducted (series 0) (Table 1).

Table 1: Different trials with different sample sizes

Trial	Sample size	Contamination	Time of initial drying
0	40	sodium chloride solution	-
1	14	Contamination of the screw with blood	60-90 min
2	40	Contamination of the screw with blood and soft tissue (muscle and fat tissue)	60-90 min
3	20	Contamination of the female thread with blood and soft tissue (muscle and fat tissue)	60-90 min
4	20	Contamination of the female thread with blood and soft tissue (muscle and fat tissue) and cleaning after drying	60-90 min

Series 1:

The influence of contamination with dried blood was examined as the components of the MRP TITAN stem get in contact with patients blood intraoperatively. Therefore the screw M6 was put into pig's blood. After blood drying the morse taper junction was fixed with the torque wrench.

Series 2:

The influence of contamination with dried blood and biologic tissue was examined as the components of the MRP TITAN stem get in contact with patients blood and soft tissue (e.g. fat, muscle tissue) intraoperatively. Therefore the screw M6 was covered with a pulpous mixture of pig's blood, pig's muscle and pig's fat tissue. After the drying process the morse taper junction was fixed with the torque wrench.

Series 3:

The influence of contamination with dried blood and biologic tissue was examined as the components of the MRP TITAN stem get in contact with patients blood and soft tissue (e.g. fat, muscle tissue) intraoperatively. Therefore the female thread component was covered with a pulpous mixture of pig's blood, pig's muscle and pig's fat tissue. After the drying process of

the female thread component a new clean M6 screw was taken out of the sterile wrapping and fixed with the torque wrench.

Series 4:

The influence of cleaning of the contaminated female thread component was examined. Therefore the female thread component was covered with a pulpous mixture of pig's blood, pig's muscle and pig's fat tissue. After the drying process of the female thread component the contamination was cleaned with 50 ml saline solution. Afterwards a new clean M6 screw was taken out of the sterile wrapping and fixed with the torque wrench.

For our in vitro study we selected a long drying phase to be sure that the drying process at 20°C was complete, knowing that intraoperatively drying process is much more faster due to manipulation of the prosthesis devices and laminar air flow.

Aim is to analyse the differences of fracture of the screw M6 (Fig. 3) in different settings (series 1-4). Due to the small sample numbers we selected Fisher's exact test for statistical analysis [23, 24]. Since there is the reasonable assumption that cleaning the interface reduces the probability of screw cracks, we use the one-sided variant of the test.



Fig.3: Torsion fracture of screw M6

3. Results

In series 1 more power was necessary to fix screw M6 using the torque wrench.

After removal of the fractured screw blood could be found within the female thread component.

In series 2 more power was necessary to fix screw M6 using the torque wrench, too. After removal of the fractured screw dried coagulum could be found within the female tread. In some cases the complete screw could be removed. In these cases, all threads showed contamination.

In series 3 fixing of screw M6 was quite easy as contamination focussed on the female

component. After removal of the fractured screw dried coagulum could be found within the female thread.

In series 4 the female thread of the morse taper junction was cleaned after contamination. Due to the cleaning process with saline solution coagulum (up to 5 mm diameter) could be removed. Inspection revealed that no complete cleaning could be achieved.

Comparing series 1 with series 4, series 2 with series 4 and series 3 with series 4 statistical analysis showed a significant reduction of fractures of screw M6. For $H_0: p_1 \leq p_4$, $H_0: p_2 \leq p_4$ and $H_0: p_3 \leq p_4$ the p-values are 0.0072, 0.0001 and 0.0042 respectively.

Cleaning of contaminated female thread of the morse taper junction leads to a significant reduction of fractures of locking screw M6 of the MRP TITAN System. In cases of cleaned components no fracture of the screw could be detected.

In cases of fractured screws removal of the distal part of the broken screw was easy possible. Analyzing surface of titanium-nitride coated screws surface of the screws showed no signs of abrasion of titanium-nitride coat.

Table 2: Tabular summary of the results.

Series	1	2	3	4
Sample size	14	40	20	20
Number of fractures	5	18	7	0
Location of fracture (No. of thread)	8-9	8-9	8-9	-
Fracture type	torsion fracture	torsion fracture	torsion fracture	-
Sound during fixing screw M6 using torque wrench	Creaking	Creaking	Creaking	Squeaking

4. Discussion

The use of modular MRP TITAN System in primary and revision arthroplasty of the hip offers a lot of advantages like optimization of femoral anteversion, limb length, and femoral component offset [1, 2, 3, 4]. Several authors discussed new problems and complications like fretting, crevice and galvanic corrosion, component loosening, fracture and dissociation of modular prostheses in primary and revision hip arthroplasty [5-17]. Grupp et al. [16] were the first who showed that surface contamination with blood or biologic tissue is a risk factor for breakage of modular components in total hip replacement. Failure of modular titanium alloy neck adapters can be initiated by surface micromotions due to surface contamination or highly

loaded implant components [16]. Another risk factor for implant failure is body weight over 100 kg which is postulated by Schuh et al., too [15]. Grupp et al. [16] recommended the use of modular cobalt chrome neck adapters which should provide higher safety compared to Titanium alloy material. Haschke H et al. [25] postulated that surgeons should carefully use assembly forces above 4 kN to decrease the amount of relative motion within the taper interface of neck adapters made of titanium (Ti6Al4V) and CoCr (CoCr29Mo).

In respect to published allergic reactions against cobalt chrome alloys [26-28] and the possible problem of local galvanic element mixing titanium and cobalt chrome alloys we don't follow this solution.

Our results clearly show that contamination of the inner tread of morse taper junction with blood or other biologic tissue leads to a significant reduction of resistance against fracture of the screw M6. Contamination can occur if the guiding rod has to be fixed several times and gets in contact with intraoperative situ. This leads to contamination of the guiding rod and the female component of the threads. Contamination leads to blocking of the screw. If fixation process of screw M6 is continued forcely using torque limiter the screw can be twisted off. In cases of fractured screws removal of the distal part of the broken screw was easy possible as blocking of the screw seems to occur in just one direction. Normally the fixation process of the titanium-nitride coated screw M6 leads to smooth abrasion of the coating as a sign of complete contact of screw with the neck. In our study no or few signs of abrasion could be detected in contaminated screws. We conclude that in cases of contamination the head of the screw does not get in contact with the neck. In that way the torsional moment of 25 Nm concentrates on the body of the screw and leads to fracture of the screw. The screw is designed to resist tensile stress not torsional stress.

5. Conclusions

Modularity in THR provides intraoperative flexibility when partial hip implant revision is required. However, modularity creates new potential problems and complications like fretting, crevice and galvanic corrosion, component loosening and fracture. To avoid fracture of the screw M6 in revisionarthroplasty of the hip using the MRP Titan System we recommend cleaning the inner tread of the morse taper junction with saline solution.

References

1. Hoberg M, Konrads C, Engelien J, Oschmann D, Holder M, Walcher M, Rudert M. Outcome of a modular tapered uncemented titanium femoral stem in revision hip arthroplasty. *Int Orthop*. 2015 Sep;39(9):1709-13
2. Schuh A, Werber S, Holzwarth U, Zeiler G. Cementless modular hip revision arthroplasty using the MRP Titan Revision Stem: outcome of 79 hips after an average of 4 years' follow-up. *Arch Orthop Trauma Surg*. 2004 Jun;124(5):306-9.
3. Wimmer MD, Randau TM, Deml MC, Ascherl R, Nöth U, Forst R, Gravius N, Wirtz D, Gravius S. Impaction grafting in the femur in cementless modular revision total hip arthroplasty: a descriptive outcome analysis of 243 cases with the MRP-TITAN revision implant. *BMC Musculoskelet Disord*. 2013 Jan 11;14:19. doi: 10.1186/1471-2474-14-19.
4. Wirtz DC, Gravius S, Ascherl R, Thorweihe M, Forst R, Noeth U, Maus UM, Wimmer MD, Zeiler G, Deml MC. Uncemented femoral revision arthroplasty using a modular tapered, fluted titanium stem: 5- to 16-year results of 163 cases. *Acta Orthop*. 2014 Dec;85(6):562-9.
5. Atwood SA, Patten EW, Bozic KJ, Pruitt LA, Ries MD. Corrosion-induced fracture of a double-modular hip prosthesis: a case report. *J Bone Joint Surg* 6:1522-1525 (2010).
6. Dangles CJ, Altstetter CJ (2010) Failure of the modular neck in a total hip arthroplasty. *J Arthroplasty* 25: 1169.e5- 7.
7. Dunbar MJ (2010) The proximal modular neck in THA: a bridge too far: affirms. *Orthopedics* 33: 640.
8. Duncan ST, Hayes CB, Nunley RM (2016) Fracture at the Modular Junction of a Cementless Revision Hip System: A Case Report. *JBJS Case Connect* 6: e48.
9. Ellman MB and Levine BR (2013) Fracture of the modular femoral neck component in total hip arthroplasty. *J Arthroplasty* 28: 196.e1-5.
10. Esposito CI, Wright TM, Goodman SB, Berry DJ. (2014) Clinical, Biological and Bioengineering Study Groups from Carl T. Brighton Workshop. What is the trouble with trunnions? *Clin Orthop Relat Res* 472: 3652-3658.
11. Lakstein D, Eliaz N, Levi O, Backstein D, Kosashvili Y, Safir O, Gross AW. (2011) Fracture of cementless femoral stems at the mid-stem junction in modular revision hip arthroplasty systems. *J Bone Joint Surg* 93: 57-65.

12. Munir S, Walter WL, Walsh WR (2015) Variations in the trunnion surface topography between different commercially available hip replacement stems. *J Orthop Res* 33: 98-105.
13. Parisi T, Burroughs B, Kwon YM (2015) Modular hip implant fracture at the stem-sleeve interface. *Orthopedics* 38: e234-9
14. Pour AE, Borden R, Murayama T, Groll-Brown M, Blaha JD (2016) High Risk of Failure With Bimodular Femoral Components in THA. *Clin Orthop Relat Res* 474: 146-53.
15. Schuh A, Sesselmann S, Scheller A, Jezussek D, Hönle W. Recurrent Fracture of the Cone of a Morse Taper Junction of the MRP Stem in an Obese Patient- A Case Report. *J Med Adv Clin Case Rep* 2020 (1):1-4
16. Grupp TM, Weik T, Bloemer W, Knaebel HP. Modular titanium alloy neck adapter failures in hip replacement-failure mode analysis and influence of implant material. *BMC Musculoskelet Disord* 2010; 11: 3
17. Fink B. What Can the Surgeon Do to Reduce the Risk of Junction Breakage in Modular Revision Stems? *Arthroplast Today*. 2018 Sep; 4(3): 306-309.
18. ASTM F136-13: Standard Specification for Wrought Titanium-6Aluminum-4 Vanadium ELI (Extra Low Interstitial) Alloy for Surgical Implant Applications (UNS S56401)
19. ISO 5832-3:2017-03. Implants for surgery - Metallic materials - Part 3: Wrought titanium 6-aluminium 4-vanadium alloy (ISO 5832-3:2016
20. ISO 7206-6:2013-11. Implants for surgery - Partial and total hip joint prostheses – Part 6: Endurance properties testing and performance requirements of neck region of stemmed femoral components
21. ISO 7206-4:2010-06. Implants for surgery - Partial and total hip joint prostheses – Part 4: Determination of endurance properties and performance of stemmed femoral components.
22. van Hove RP, Sierevelt IN, van Royen BJ, Nolte PA. Titanium-Nitride Coating of Orthopaedic Implants: A Review of the Literature. *Biomed Res Int*. 2015;2015:485975. doi: 10.1155/2015/485975.
23. Pfanzagl J, Allgemeine Methodenlehre der Statistik, Band II, 3. Auflage, Berlin 1968.
24. Bortz J, Lienert GA, Boehnke K, Verteilungsfreie Methoden in der Biostatistik. 3. Auflage. Berlin Heidelberg 2008.

25. Haschke H, Jauch-Matt SY, Sellenschloh K, Huber G, Morlock MM. Assembly force and taper angle difference influence the relative motion at the stem-neck interface of bi-modular hip prostheses. *Proc Inst Mech Eng H*. 2016 Jul;230(7):690-9
26. D'Angelo F, Tanas D, Gallazzi E, Zagra L. Adverse reaction to metal debris after small-head diameter metal-on-metal total hip arthroplasty: an increasing concern. *Hip Int* 2018 Nov;28(2_suppl):35-42.
27. Thomas P, Weik T, Roeder G, Summer B, Thomsen M. Influence of Surface Coating on Metal Ion Release: Evaluation in Patients with Metal Allergy. *Orthopedics* 2016 May;39(3 Suppl):24-30. doi: 10.3928/01477447-20160509-08.
28. Hopf F, Thomas P, Sesselmann S, Thomsen M, Hopf M, Hopf J, Krukemeyer MG, Resch H, Krenn V. CD3+ lymphocytosis in the peri-implant membrane of 222 loosened joint endoprostheses depends on the tribological pairing. *Acta Orthop* 2017 Dec;88(6):642-648.
29. Krüger, D., Günther, KP., Deml, M., Perka, C. (2020). Mechanical failure of 113 uncemented modular revision femoral components risk factors for fracture and failure with a case control comparison analysis. *Bone and Joint Journal*. 102-B. 573–579. 10.1302/0301-620X.102B5.BJJ-2019-1333.R2.

Bisher erschienene Weidener Diskussionspapiere

- 1** „Warum gehen die Leute in die Fußballstadien? Eine empirische Analyse der Fußball-Bundesliga“
von Horst Rottmann und Franz Seitz
- 2** „Explaining the US Bond Yield Conundrum“
von Harm Bandholz, Jörg Clostermann und Franz Seitz
- 3** „Employment Effects of Innovation at the Firm Level“
von Horst Rottmann und Stefan Lachenmaier
- 4** „Financial Benefits of Business Process Management“
von Helmut Pirzer, Christian Forstner, Wolfgang Kotschenreuther und Wolfgang Renninger
- 5** „Die Performance Deutscher Aktienfonds“
von Horst Rottmann und Thomas Franz
- 6** „Bilanzzweck der öffentlichen Verwaltung im Kontext zu HGB, ISAS und IPSAS“
von Bärbel Stein
- 7** Fallstudie: „Pathologie der Organisation“ – Fehlentwicklungen in Organisationen, ihre Bedeutung und Ansätze zur Vermeidung
von Helmut Klein
- 8** „Kürzung der Vorsorgeaufwendungen nach dem Jahressteuergesetz 2008 bei betrieblicher Altersversorgung für den GGF.“
von Thomas Dommermuth
- 9** „Zur Entwicklung von E-Learning an bayerischen Fachhochschulen- Auf dem Weg zum nachhaltigen Einsatz?“
von Heribert Popp und Wolfgang Renninger
- 10** „Wie viele ausländische Euro-Münzen fließen nach Deutschland?“
von Dietrich Stoyan und Franz Seitz
- 11** Modell zur Losgrößenoptimierung am Beispiel der Blechteilindustrie für Automobilzulieferer
von Bärbel Stein und Christian Voith
- 12** Performancemessung
Theoretische Maße und empirische Umsetzung mit VBA
von Franz Seitz und Benjamin R. Auer
- 13** Sovereign Wealth Funds – Size, Economic Effects and Policy Reactions
von Thomas Jost

- 14 The Polish Investor Compensation System Versus EU – 15 Systems and Model Solutions
von Bogna Janik**
- 15 Controlling in virtuellen Unternehmen -eine Studie-
Teil 1: State of the art
von Bärbel Stein, Alexander Herzner, Matthias Riedl**
- 16 Modell zur Ermittlung des Erhaltungsaufwandes von Kunst- und Kulturgütern in
kommunalen Bilanzen
von Bärbel Held**
- 17 Arbeitsmarktinstitutionen und die langfristige Entwicklung der Arbeitslosigkeit –
Empirische Ergebnisse für 19 OECD-Länder
von Horst Rottmann und Gebhard Flaig**
- 18 Controlling in virtuellen Unternehmen -eine Studie-
Teil 2: Auswertung
von Bärbel Held, Alexander Herzner, Matthias Riedl**
- 19 DIAKONIE und DRG's –antagonistisch oder vereinbar?
von Bärbel Held und Claus-Peter Held**
- 20 Traditionelle Budgetierung versus Beyond Budgeting-
Darstellung und Wertung anhand eines Praxisbeispiels
von Bärbel Held**
- 21 Ein Factor Augmented Stepwise Probit Prognosemodell
für den ifo-Geschäftserwartungsindex
von Jörg Clostermann, Alexander Koch, Andreas Rees und Franz Seitz**
- 22 Bewertungsmodell der musealen Kunstgegenstände von Kommunen
von Bärbel Held**
- 23 An Empirical Study on Paths of Creating Harmonious Corporate Culture
von Lianke Song und Bernt Mayer**
- 24 A Micro Data Approach to the Identification of Credit Crunches
von Timo Wollmershäuser und Horst Rottmann**
- 25 Strategies and possible directions to improve Technology
Scouting in China
von Wolfgang Renninger und Mirjam Riesemann**
- 26 Wohn-Riester-Konstruktion, Effizienz und Reformbedarf
von Thomas Dommermuth**
- 27 Sorting on the Labour Market: A Literature Overview and Theoretical Framework
von Stephan O. Hornig, Horst Rottmann und Rüdiger Wapler**
- 28 Der Beitrag der Kirche zur Demokratisierungsgestaltung der Wirtschaft
von Bärbel Held**

- 29 Lebenslanges Lernen auf Basis Neurowissenschaftlicher Erkenntnisse
-Schlussfolgerungen für Didaktik und Personalentwicklung-
von Sarah Brückner und Bernt Mayer**
- 30 Currency Movements Within and Outside a Currency Union: The case of Germany
and the euro area
von Franz Seitz, Gerhard Rösl und Nikolaus Bartzsch**
- 31 Labour Market Institutions and Unemployment. An International Comparison
von Horst Rottmann und Gebhard Flaig**
- 32 The Rule of the IMF in the European Debt Crisis
von Franz Seitz und Thomas Jost**
- 33 Die Rolle monetärer Variablen für die Geldpolitik vor, während und nach der Krise:
Nicht nur für die EWU geltende Überlegungen
von Franz Seitz**
- 34 Managementansätze sozialer, ökologischer und ökonomischer Nachhaltigkeit:
State of the Art
von Alexander Herzner**
- 35 Is there a Friday the 13th effect in emerging Asian stock markets?
von Benjamin R. Auer und Horst Rottmann**
- 36 Fiscal Policy During Business Cycles in Developing Countries: The Case of Africa
von Willi Leibfritz und Horst Rottmann**
- 37 MONEY IN MODERN MACRO MODELS: A review of the arguments
von Markus A. Schmidt und Franz Seitz**
- 38 Wie erzielen Unternehmen herausragende Serviceleistungen mit höheren Gewinnen?
von Johann Strassl und Günter Schicker**
- 39 Let's Blame Germany for its Current Account Surplus!?
von Thomas Jost**
- 40 Geldpolitik und Behavioural Finance
von Franz Seitz**
- 41 Rechtliche Überlegungen zu den Euro-Rettungsschirmprogrammen und den
jüngsten geldpolitischen Maßnahmen der EZB
von Ralph Hirdina**
- 42 DO UNEMPLOYMENT BENEFITS AND EMPLOYMENT PROTECTION INFLUENCE
SUICIDE MORTALITY? AN INTERNATIONAL PANEL DATA ANALYSIS
von Horst Rottmann**

- 43 Die neuen europäischen Regeln zur Sanierung und Abwicklung von Kreditinstituten: Ordnungspolitisch und rechtlich angreifbar?
von Ralph Hirdina**
- 44 Vermögensumverteilung in der Eurozone durch die EZB ohne rechtliche Legitimation?
von Ralph Hirdina**
- 45 Die Haftung des Steuerzahlers für etwaige Verluste der EZB auf dem rechtlichen Prüfstand
von Ralph Hirdina**
- 46 Die Frage nach dem Verhältnis von Nachhaltigkeit und Ökonomie
von Alexander Herzner**
- 47 Giving ideas a chance - systematic development of services in manufacturing industry
von Johann Strassl, Günter Schicker und Christian Grasser**
- 48 Risikoorientierte Kundenbewertung: Eine Fallstudie
von Thorsten Hock**
- 49 Rechtliche Überlegungen zur Position der Sparer und institutionellen Anleger mit Blick auf die Niedrigzins- bzw. Negativzinspolitik der Europäischen Zentralbank
von Ralph Hirdina**
- 50 Determinanten des Studienerfolgs: Eine empirische Untersuchung für die Studiengänge Maschinenbau, Medienproduktion und -technik sowie Umwelttechnik
von Bernd Rager und Horst Rottmann**
- 51 Cash Holdings in Germany and the Demand for "German" Banknotes: What role for cashless payments
von Nikolaus Bartzsch und Franz Seitz**
- 52 Europäische Union und Euro – Wie geht es weiter? – Rechtliche Überlegungen
von Ralph Hirdina**
- 53 A Call for Action – Warum sich das professionelle Management des Service Portfolios in der Industrie auszahlt
von Günter Schicker und Johann Strassl**
- 54 Der Studienerfolg an der OTH Amberg-Weiden – Eine empirische Analyse der Studiengänge Maschinenbau, Medienproduktion und Medientechnik sowie Umwelttechnik
von Bernd Rager und Horst Rottmann**
- 55 Die Bewertung von Aktienanleihen mit Barriere – Eine Fallstudie für die Easy-Aktienanleihe der Deutschen Bank
von Maurice Hofmann und Horst Rottmann**
- 56 Studie: Die Generation Y und deren organisatorische Implikationen
von Helmut Klein**

- 57 **Die gesetzliche Einschränkung von Bargeldzahlungen und die Abschaffung von Bargeld auf dem rechtlichen Prüfstand**
von Ralph Hirdina
- 58 **Besser ohne Bargeld? Gesamtwirtschaftliche Wohlfahrtsverluste der Bargeldabschaffung**
von Gerhard Rösl, Franz Seitz, Karl-Heinz Tödter
- 59 **Nowcasting des deutschen BIP**
von Jens Doll, Beatrice Rosenthal, Jonas Volkenand, Sandra Hamella
- 60 **Herausforderungen und Erfolgsfaktoren bei der Einführung Cloud-basierter Unternehmenssoftware – Erfahrungen aus der Praxis**
von Thomas Dobat, Stefanie Hertel, Wolfgang Renninger
- 61 **Global Recessions and Booms: What do Probit models tell us?**
von Ursel Baumann, Ramón Gómez Salvador, Franz Seitz
- 62 **Feste Zinsbindung versus kurzfristig variable Zinskonditionen in Deutschland**
von Jörg Clostermann und Franz Seitz
- 63 **Deferred-Compensation-Modelle: Ersatz für eine konventionelle betriebliche Altersversorgung nach dem Betriebsrentengesetz?**
von Thomas Dommermuth und Thomas Schiller
- 64 **Have capital market anomalies worldwide attenuated in the recent era of high liquidity and trading activity?**
von Benjamin R. Auer und Horst Rottmann
- 65 **Vorschläge des französischen Staatspräsidenten Emmanuel Macron zur Reform der Europäischen Union**
von Ralph Hirdina
- 66 **Von der Troika zu einem Europäischen Währungsfonds – Welche Aufgaben und Grenzen sollte ein Europäischer Währungsfonds nach den Erfahrungen mit der Troika haben?**
von Thomas Jost
- 67 **Does Microfinance have an impact on borrower's consumption patterns and women's empowerment?**
von Charlotte H. Feldhoff, Yi Liu und Patricia R. Feldhoff
- 68 **Uncertainty in the Black-Litterman Model - A Practical Note**
von Adrian Fuhrer und Thorsten Hock
- 69 **Produktportfolio-Management im Zeitalter der Digitalisierung**
von Günter Schicker und Johann Strassl
- 70 **Evaluation eines Inverted Classroom Konzepts in der makroökonomischen Lehre**
von Horst Rottmann und Christoph Voit
- 71 **Immobilienkredite in Deutschland und der Schweiz: Die Rolle von Zinsen und Zinsbindung**
von Jörg Clostermann und Franz Seitz

- 72** **Intelligente Verpackungen**
von **Stephanie Abels-Schlosser**
- 73** **Digitale Strategien entwickeln – von der Idee zur Roadmap**
von **Johann Strassl und Günter Schicker**
- 74** **Derivate im Zinsmanagement: Eine Analyse der Hedging-Qualität von Bund Future**
Kontrakten und deren Einsatzmöglichkeiten in Theorie und Praxis
von **Christoph Wontke und Franz Seitz**
- 75** **Steigerung der Kundenzufriedenheit durch Gestaltung von Artikeldetailseiten**
am Beispiel von WITT WEIDEN
von **Laura Graser und Marco Nirschl**
- 76** **Werkvertragsarbeitnehmerinnen und -arbeitnehmer in der Fleischindustrie**
von **André Schulte und Ágnes Wörster**
- 77** **How to avoid fracture of the locking screw in modular revision arthroplasty of the hip**
using the MRP Titan Revision System
von **Theresa Semmelmann, Alexander Schuh, Horst Rottmann, Reinhard Schröder,**
Christopher Fleischmann



Ostbayerische Technische Hochschule
Amberg-Weiden

Die Weidener Diskussionspapiere erscheinen in unregelmäßigen Abständen und sollen Erkenntnisse aus Forschung und Wissenschaft an der Hochschule in Weiden insbesondere zu volks- und betriebswirtschaftlichen Themen an Wirtschaft und Gesellschaft vermitteln und den fachlichen Dialog fördern.

Herausgeber:

Ostbayerische Technische Hochschule (OTH) Amberg-Weiden
Prof. Dr. Horst Rottmann und Prof. Dr. Franz Seitz
Fakultät Betriebswirtschaft

Presserechtliche Verantwortung:

Sonja Wiesel, Hochschulkommunikation und Öffentlichkeitsarbeit
Telefon +49 (9621) 482-3135
Fax +49 (9621) 482-4135
s.wiesel@oth-aw.de

Bestellungen schriftlich erbeten an:

Ostbayerische Technische Hochschule Amberg-Weiden
Abt. Weiden, Bibliothek
Hetzenrichter Weg 15,
D – 92637 Weiden i.d.Opf.

Die Diskussionsbeiträge können elektronisch abgerufen werden unter
http://www.oth-aw.de/aktuelles/veroeffentlichungen/weidener_diskussionspapiere/

Alle Rechte, insbesondere das Recht der Vervielfältigung und Verbreitung sowie Übersetzung vorbehalten.
Nachdruck nur mit Quellenangabe gestattet.

ISBN 978-3-937804-79-8

- **Abteilung Amberg:** Kaiser-Wilhelm-Ring 23, 92224 Amberg,
Tel.: (09621) 482-0, Fax: (09621) 482-4991
- **Abteilung Weiden:** Hetzenrichter Weg 15, 92637 Weiden i. d. OPf.,
Tel.: (0961) 382-0, Fax: (0961) 382-2991
- **E-Mail:** info@oth-aw.de | **Internet:** <http://www.oth-aw.de>